

COVERLAST FT

Technical sheet



CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Composition	100% polyester			
Backing / Finish	acrylique coating one side			
Weight	250		g/m ²	ISO 3801
Width	152		cm	EN 1773
Roll length	60		ml	

FABRIC RESISTANCE

Tensile strength	195	104	daN/5cm	ISO 13934-1
Elongation at break	22.5	22.9	%	ISO 13934-1
Tear strength	6	3	daN	ISO 13937-1
Schmerber	> 2500		mm	ISO 811
Spray test	5		Class / 5	ISO 4920
Oil-resistance properties	0		Class / 8	ISO 14419

COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	CLA5 ISO 105 B04	Class / 5	ISO 105 B04
--------------------------------------	------------------	-----------	-------------

USES

Guarantee	3	years	
-----------	---	-------	--

This product's values may vary with a tolerance of $\pm 5\%$

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK

WARRANTY

3

YEARS

**NON
PFAS**